

BS75K

Low Oil-Bleeding Thermal Conductive Gel

LiPOLY BS75K is a soft thermally conductive gap filler. With a thermal conductivity of 3.0 W/m*K and a low thermal impedance, BS75K is suitable for a wide range of applications. This product can be supplied as standard sheets, custom die-cuts or custom molded parts making it suitable for a wide range of applications. BS75K is also UL 94V-0 approved and REACH and RoHS compliant.

Features-


- Thermal conductivity:3.0W/m*K
- Naturally tacky for ease of manufacture
- Highly compliant
- Low thermal impedance
- Available in a range of thicknesses

Typical Applications-

- Notebook computers
- Heat pipe assemblies
- TV hardware
- Automotive electronics
- Mobile devices
- High speed mass storage drives
- Set top box
- IP CAM

Specifications-

- Sheet form
- Die-cut parts



Typical Properties-

PROPERTY	BS75K	TEST METHOD	UNIT
Color	Dark Gray	Visual	-
Surface tack 2-side/1-side	2	-	-
Thickness	Customized	ASTM D374	mm
Density	2.5	ASTM D792	g/cm ³
Hardness	18	ASTM D2240	Shore OO
Application temperature	-60~180	-	°C
COMPRESSION@1.0mm			
Deflection @10 psi	35	ASTM D5470 modify	%
Deflection @20 psi	39	ASTM D5470 modify	%
Deflection @30 psi	43	ASTM D5470 modify	%
Deflection @40 psi	46	ASTM D5470 modify	%
Deflection @50 psi	48	ASTM D5470 modify	%
ELECTRICAL			
Dielectric breakdown	8	ASTM D149	KV/mm
Surface resistivity	>10 ¹⁰	ASTM D257	Ohm
Volume resistivity	>10 ¹¹	ASTM D257	Ohm-m
THERMAL			
Thermal Conductivity	3.0	ASTM D5470	W/m*K
Thermal impedance@10psi	0.56	ASTM D5470	°C-in ² /W
Thermal impedance@30psi	0.50	ASTM D5470	°C-in ² /W
Thermal impedance@50psi	0.46	ASTM D5470	°C-in ² /W
FLAME RATING			
UL Flammability class	V-0	UL94	-

Oil Bleeding-

Size 30*30mm²
 Thickness 1.0mm
 Compression 50%
 Temperature 25°C
 Time 120h

